

PROLITE® RAPID SETTING TILE & STONE MORTAR

1. Product Name

ProLite® Rapid Setting Tile & Stone Mortar

2. Manufacturer

Custom Building Products
13001 Seal Beach Blvd.
Seal Beach, CA 90740-2757
Customer Support: 800-272-8786
Technical Services: 800-282-8786
Fax: 800-200-7765
Email: contactus@cbpmail.net
custombuildingproducts.com

3. Product Description

Industry-leading ProLite Rapid Setting Tile & Stone Mortar is a lightweight, medium bed, rapid-setting mortar. This technologically advanced mortar offers high-performance and flexibility designed to meet the rigors of setting large format tile and stone for fast track commercial or residential installations. Capable of thin-set or medium bed application up to 3/4" (19 mm) thick on horizontal surfaces after beat-in. Adjustments allowed, yet it will set quickly — allowing the grouting process to begin in under 3 hours with light traffic in 4 hours. 1-part formula with no need for a separate liquid additive to improve bonds strength, flexibility or performance. ProLite Rapid Setting is ready to perform by simply adding water. Excellent open time and adjustability. Non-slump performance for floor installations. Formulated with CustomLite® Technology, ProLite is 40% lighter than traditional mortars, providing excellent handling characteristics. A 30 lb. (13.6 kg) bag covers the same area as a 50 lb. (22.68 kg) bag of traditional mortar. Formulated with recycled material — contributes to LEED® certification. Exceeds ANSI A118.4 and A118.11 without the need for additives.

ProLite Rapid Setting can be used with the following tile types:

- Vitreous, semi-vitreous or non-vitreous tile: ceramic, mosaic, quarry, cement body tile
- Impervious porcelain and glass tile
- Brick and thin brick
- Precast cement-based terrazzo
- Natural stone tile

ProLite Rapid Setting can be used with the following substrates:

- Concrete, mortar beds, masonry, Portland cement plaster
- WonderBoard®, cement backerboards
- Liquid applied waterproofing membranes such as RedGard® and Custom 9240®



- Crack prevention sheet membranes such as Crack Buster Pro®
- Exterior grade plywood (interior residential and light commercial dry areas)
- Gypsum wallboard (interior dry areas)
- Existing ceramic tile
- Fully bonded sheet vinyl flooring
- Plastic laminates
- Cutback adhesive

COMPOSITION & MATERIALS

ProLite Rapid Setting is a dry, proprietary blend of copolymers, Portland cement, inorganic aggregates and chemicals.

BENEFITS

- Sets quickly — Allows grouting in as little as 2 – 3 hours and foot traffic in 4 hours
- Maximum bond strength and flexibility
- Non-slump medium bed for heavy tile and stone installations for floors and walls
- Exceeds ANSI A118.4 and A118.11 standards without the need for additives

LIMITATIONS

- Do not bond directly to hardwood, lauan plywood, particle board, parquet, cushion or sponge back vinyl flooring, metal, fiberglass, plastic or OSB panels.
- When setting moisture sensitive natural stone, cement or agglomerate tile, check with Custom Building Products; use EBM-Lite™ Epoxy Bonding Mortar—100% Solids or CEG-Lite™ 100% Solids Commercial Epoxy Grout.
- When setting resin backed stone, check with Custom Building Products; use EBM-Lite™ Epoxy Bonding Mortar—100% Solids or CEG-Lite™ 100% Solids Commercial Epoxy Grout.



- When setting glass tile larger than 6" x 6" (15 x 15 cm), contact Custom Building Products for recommendations.
- When setting dimensional stone larger than 12" x 12" (30 x 30 cm), contact Custom Building Products for recommendations regarding subfloor deflection requirements.
- Do not use to control vertical movement cracks.
- Do not use to bridge or cover over existing expansion or construction joints.
- Do not apply directly to lightweight concrete or gypsum based underlayments. See Section 5 for preparatory instructions.
- For manufacturing facilities where heavy solvents are used, consult Custom Building Products.

PACKAGING

- 30 lb (13.6 kg) bag
- Gray or white

4. Technical Data

APPLICABLE STANDARDS

American National Standards Institute (ANSI) — ANSI A108.5, A118.4 and A118.11 of the American National Standards for the Installation of Ceramic Tile

ASTM International (ASTM)

- ASTM C109 Standard Test Method for Compressive Strength of Hydraulic Cement Mortars (Using 2-in. or (50-mm) Cube Specimens)
- ASTM C627 Standard Test Method for Evaluating Ceramic Floor Tile Installation Systems Using the Robinson-Type Floor Tester

Resilient Floor Covering Institute (RFCI) — Recommended Work Practices for Removal of Resilient Floor Coverings

Tile Council of North America (TCNA) — TCNA Handbook for Ceramic Tile Installation, TCNA Method EJ171

TECHNICAL PROPERTIES

Results based on applicable ANSI test specifications

Property	Results
Pot life	40 – 60 minutes
Open time	20+ minutes
Adjustment time	20+ minutes
Shear bond @ 28 days	
Bisque tile	600 psi (42.2 kg/cm ²)
Porcelain Tile	425 psi (29.9 kg/cm ²)
Quarry tile to plywood	250 psi (17.6 kg/cm ²)

ENVIRONMENTAL CONSIDERATIONS

Custom Building Products is committed to environmental responsibility in both products produced and in manufacturing practices.

Use of ProLite Rapid Setting can contribute to LEED® certification.

5. Installation

PREPARATORY WORK

General Surface Preparation:

Surfaces must be structurally sound, clean, dry and free from grease, oil, dirt, curing compounds, sealers, adhesives and other contaminants that would prevent a good bond. Glossy or painted surfaces must be sanded, stripped and cleaned of waxes, dirt and other contaminants. Ambient temperature, surfaces and materials should be 50° – 100° F (10° – 38° C) for 72 hours.

Cementitious Surfaces:

Concrete or plaster must be fully cured and must accept water penetration. Test by sprinkling water on various areas of the substrate. If water penetrates, then a good bond can be achieved; if water beads, surface contaminants are present, and loss of adhesion may occur. Contaminants should be mechanically removed before installation. Concrete must be free of efflorescence and not subject to hydrostatic pressure. Concrete slabs should have a broomed or brushed finish to enhance the bond. Smooth concrete slabs must be mechanically abraded to ensure a good bond.

Lightweight, Gypsum Based Underlayments:

Lightweight or gypsum based underlayments must first be treated with RedGuard® Waterproofing and Crack Prevention Membrane and must obtain a minimum 2000 psi (13.8 MPa) compressive strength at the recommended cure time.

The underlayment must be sufficiently dry and properly cured to the manufacturer’s specifications for permanent, non-moisture permeable coverings. Surfaces to be tiled must be structurally sound and subject to deflection not to exceed the current ANSI standards.

All lightweight concrete and gypsum based underlayment surfaces to receive RedGuard must be primed with properly applied sealer or a primer coat of RedGuard, consisting of 1 part RedGuard diluted with 4 parts clean, cool water. Mix in a clean bucket at low speed to obtain a lump free solution. The primer can be brushed, rolled or sprayed to achieve an even coat. Apply the primer coat to the floor at a rate of 300 ft²/gal (7.5 M²/L). Drying time depends on site conditions, but is normally less than 1 hour. Extremely porous surfaces may require 2 coats.

At this point, RedGuard can be applied to the primed lightweight or gypsum based surface. Refer to the individual product data sheet or packaging directions for application instructions.

Expansion joints must be installed in accordance with local building codes and ANSI/TCNA guidelines. Refer to TCNA EJ171.



Plywood Substrates:

Plywood floors, including those under resilient flooring, must be structurally sound and must meet all ANSI and deflection requirements. For questions about proper sub floor installation, call Custom Building Products.

WonderBoard Backerboard:

As an alternative to an additional layer of plywood, WonderBoard backerboard may be installed over plywood subfloors. Refer to TCNA F144.

Existing Ceramic Tile, Resilient Flooring or Plastic Laminates:

Plywood flooring must be structurally sound and must meet all ANSI and deflection requirements. Resilient flooring or plastic laminates must be well bonded, as well as clean and free of all contaminates. Roughen the surface by sanding or scarifying; rinse and allow to dry. Do not sand flooring that contains asbestos. For existing well bonded ceramic tile, mechanically abrade the surface. Rinse and allow to dry. When sanding, an approved respirator should be used.

Cutback Adhesive Over Concrete:

Adhesive layers must be removed, as they reduce mortar bond strength to cement surfaces. Use extreme caution; adhesives may contain asbestos fibers. Do not sand or grind adhesive residue, as harmful dust may result. Never use adhesive removers or solvents, as they soften the adhesive and may cause it to penetrate into the concrete. Adhesive residue must be wet scraped to the finished surface of the concrete, leaving only the transparent staining from the glue. To determine desirable results, do a test bond area before starting. Refer to the RFCI Pamphlet, "Recommended Work Practices for Removal of Resilient Floor Coverings" for further information.

Expansion Joints:

Expansion joints and cold joints, as described in ANSI A108.01, should never be bridged with setting material. They must be brought through the tile work and filled with an appropriate elastomeric sealant. Contact Custom Building Products for the proper treatment of control or saw cut joints. Refer to TCNA EJ171, F125 or F125A.

METHODS

Mixing

Mix 5.5 qt (5.21 L) clean water to 30 lb (13.6 kg) bag of mortar.

Mix by hand or use a low 150 - 200 rpm speed 1/2" (13 mm) drill to achieve a smooth, paste-like consistency. Let the mixture slake or stand 5 - 10 minutes; stir again and use. Stir occasionally, but do not add more water. When properly mixed, troweled ridges will stand without slump.

Application

Installation must conform to ANSI A108.5. Use a properly sized notch trowel to ensure proper coverage under tiles.

Using the flat side of the trowel, apply a skim coat of mortar to the surface. With the notch side of the trowel held at a 45° angle, apply additional mortar to the surface, combing in one direction.

Press the tile firmly into place in a perpendicular motion across ridges, moving back and forth. The perpendicular motion flattens ridges and closes valleys, allowing maximum coverage. With some tile, back buttering is advisable.

Adjust the tile promptly and beat it in with a block and rubber mallet.

Periodically pull up a tile and check the back to ensure proper adhesive coverage. Do not spread more material than can be tiled within 10 minutes or while material has a wet tack (sticky to the touch). If the material has skinned over (not sticky), re-comb with the notch trowel; if too dry, remove and replace the dry material with fresh material.

Coverage

SQUARE FOOT COVERAGE PER 30 LB BAG (SQUARE METER PER 13.6 KG)	
TROWEL SIZE	COVERAGE
1/4" x 1/4" x 1/4" (6 x 6 x 6 mm) Square-Notch	90 - 100 sq. ft. (8.4 - 9.3 M ²)
1/4" x 3/8" x 1/4" (6 x 9.5 x 6 mm) Square-Notch	63 - 70 sq. ft. (5.8 - 6.5 M ²)
1/2" x 1/2" x 1/2" (13 x 13 x 13 mm) Square-Notch	45 - 50 sq. ft. (4.2 - 4.6 M ²)
3/4" x 9/16" x 3/8" (19 x 14 x 9.5 mm) U-Notch	36 - 40 sq. ft. (3.3 - 3.7 M ²)

Curing

Curing time is affected by ambient and surface temperatures and humidity. Use the following as a guideline.

Allow 2 to 2.5 hours before grouting and 4 - 6 hours before light traffic.

Cleaning

Clean with water before the material dries.

PRECAUTIONS

This product contains Portland cement and free silica. Avoid eye contact or prolonged contact with skin. Wash thoroughly after handling. If eye contact occurs, flush with water for 15 minutes and consult a physician. Do not breathe dust; wear a NIOSH approved respirator



BUILDING CODES

Installation must comply with the requirements of all applicable local, state and federal code jurisdictions.

6. Availability & Cost

Contact the manufacturer or visit custombuildingproducts.com for information about product cost and availability.

	ITEM CODE	SIZE	COLOR	PACKAGE
USA	PLRSW30	30 lb (13.6 kg)	White	Bag
USA	PLRSG30	30 lb (13.6 kg)	Gray	Bag
Canada	CPLRSW30	30 lb (13.6 kg)	White	Bag

7. Limited Product Warranty

This product is eligible for Custom Building Products 10 Year Installation Systems Warranty.

Custom Building Products warrants to the original consumer purchaser that its product shall be free from defects in material and workmanship under normal and proper usage for a period of one year following the date of original purchase. Custom’s sole liability under this warranty shall be limited to the replacement of the product. Some states, countries or territories do not allow the exclusion or limitation of incidental or consequential damages, so the above limitation or exclusion may not apply to you. This warranty will not extend to any product which has been modified in any way or which has not been used in accordance with Custom’s printed instructions. Custom makes no other warranties either expressed or implied. This warranty gives you specific legal rights, and you may have other rights that vary from state to state or from one country/territory to another.

For details and complete warranty information, visit custombuildingproducts.com.

8. Maintenance

Properly installed product requires no special maintenance.

9. Technical Services

For technical assistance, contact Custom Building Products or visit custombuildingproducts.com.

10. Filing Systems

Additional product information is available from the manufacturer upon request.

Related Products

Polyblend® Grout

LEED is a Registered Trademark of U.S.G.B.C

